



product
data sheet.



tel: +61 3 9303 4750
www.danielrobertson.com.au

Product Range: Traditional 76mm	
	
Product Name: Traditional Apricot	



This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots. AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	
Average Weight / Unit	3.4kg
Units per square metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc)	>15 MPa
Cold Water Absorption	<11.5%
Initial Rate of Absorption (IRA) Gross	0.5 - 2.0kg/m ² min
Estimated 15 year Coefficient of Expansion (e factor)	<1.0
Durability Class	
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Core Perforation (%)	<20
Solar Absorptance Rating	Medium

product
data sheet.



tel: +61 3 9303 4750
www.danielrobertson.com.au

Product Range: Traditional 76mm	
	
Product Name: Traditional Buff	

This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots. AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	
Average Weight / Unit	3.3kg
Units per square metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc)	>15 MPa
Cold Water Absorption	<12%
Initial Rate of Absorption (IRA) Gross	1.5 - 3.0kg/m ² min
Estimated 15 year Coefficient of Expansion (e factor)	<1.0
Durability Class	
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Core Perforation (%)	<20
Solar Absorptance Rating	Dark